



# TANEX Vladislav, a. s.

Vladislav 70, PSČ 675 01 Vladislav  
CZECH REPUBLIC

Quality management Laboratory

## Test of laboratory

Atest no :	
Product :	Hide glue Topaz I
Quantity :	
	Specification

Parameter	Method	Results
Viscosity 12,5% (mPas)	DIN ISO EN 9665	8,0-9,0
Viscosity 17,7% (°E)	TP - 03/95	3,9-5,0
Jelly strenght (Blg)	DIN ISO EN 9665	240-260
pH - value	DIN ISO EN 9665	5,5-7,5
Water content (%)	DIN ISO EN 9665	10,0-15,0
Grease content (%)	DIN ISO EN 9665	max.1,5
Ash content (%)	DIN ISO EN 9665	max.3
Foaming (ml)	TP - 03/95	-
Decomposition (%)	TP - 03/95	0-25

Date: 1.12.2014

Signature: Ambrosková