



TANEX Vladislav, a. s.

Vladislav 70, PSČ 675 01 Vladislav
CZECH REPUBLIC

Quality management Laboratory

Test of laboratory

Atest no :	
Product :	Hide glueTopaz II
Quantity :	ground, granulated
	Specification

Parameter	Method	Results
Viscosity 12,5% (mPas)	DIN ISO EN 9665	6,8 – 8,0
Viscosity 17,7% (°E)	TP - 03/95	2,9 – 3,8
Jelly strenght (Blg)	DIN ISO EN 9665	200 – 240
pH - value	DIN ISO EN 9665	5,5 – 7,5
Water content (%)	DIN ISO EN 9665	max 15
Grease content (%)	DIN ISO EN 9665	max 1,5
Ash content (%)	DIN ISO EN 9665	max 3
Foaming (ml)	TP - 03/95	-
Decomposition (%)	TP - 03/95	0-25

Date: 1.12.2014

Signature: Ambrosková